

SECTION 703

AGGREGATES

Special Provision

703-2.03 AGGREGATE FOR BASE AND SURFACE COURSE.

Add the following:

For E-1, use screened stone or screened gravel, consisting of sound, tough, durable pebbles or rock fragments of uniform quality.

Delete the last column in Table 703-2 and substitute the following:

TABLE 703-2
AGGREGATE GRADATION FOR BASE AND SURFACE COURSE
(Percent Passing By Weight)

Sieve Designation	Grading E-1
1 ½ inch	100
1 inch	
¾ inch	70-100
⅜ inch	50-85
No. 4	35-75
No. 8	20-60
No. 30	
No. 50	15-30
No. 200	7-15

For projects using type IIA selected material also used in Anchorage, add the following subsection:

703-2.17 BORROW, TYPE IIA. Material shall contain no lumps, frozen material, organic matter, or other deleterious matter, and shall be durable and sound. Meet the following gradation:

TABLE 703-15

GRADATION FOR BORROW, TYPE IIA

Sieve Designation	Cumulative Percent Passing By Weight
3"	100
¾"	50-100
#4	25-60
#10	15-50
#40	4-30
#200	2-6

In addition to the grading limits listed above, the fraction of material passing the #200 sieve shall not be greater than twenty percent (20%) of that fraction passing the #4 sieve.